

# ITW SHAKEPROOF INDUSTRIAL PRODUCTS

FINISH  
CODE

REVISION  
LEVEL

**BRIEF DESCRIPTION:**

CP-0 E CAD-DICHROMATE-WAX

**CP**

**0**

REV DATE: 4/1/2007

**GENERAL DESCRIPTION**

.0003 MINIMUM CADMIUM AND DICHROMATE PLUS WAX

**APPEARANCE**

GLOSSY YELLOW IN COLOR

**ADHESION AND DUCTILITY**

TO BE TESTED IN ACCORDANCE TO ASTM B571 (SCOTCH TAPE TEST)

**CORROSION REQUIREMENTS**

RED RUST: 120

WHITE CORRIOSION: 100

**COATING THICKNESS REQUIREMENTS**

MIN THICKNESS: .0003                      MAX THICKNESS: .0005  
THICKNESS SHALL BE TESTED PER ASTM E376

**STRESS RELIEF**

PARTS TO BE BAKED AT 400 DEGREES F FOR 4 HOURS WITHIN 1 HOUR OF BASE PLATING

**QUALITY CONTROL**

VISUALLY INSPECT FOR UNIFORMITY OF COLOR & SURFACE APPEARANCE, FREEDOM FROM TEARS, BARE SPOTS, POWDERY FILM. SLOUGHING OFF OF FILM & BLISTERING

**PROCESS TO**

QQ-P-416 TYPE II CLASS 2

PRINT DATE:

6/2/2016