

# ITW SHAKEPROOF INDUSTRIAL PRODUCTS

FINISH  
CODE

REVISION  
LEVEL

**BRIEF DESCRIPTION:**

KW-0 MAGNI 565 BLACK

**KW**

**0**

REV DATE: 3/7/2018

**GENERAL DESCRIPTION**

MAGNI 565 (ALUMINUM-RICH ORGANIC TOP COAT OVER A ZINC-RICH INORGANIC BASE COAT)

**APPEARANCE**

BLACK APPEARANCE

**ADHESION AND DUCTILITY**

TO BE TESTED IN ACCORDANCE TO ASTM B571 (SCOTCH TAPE TEST)

**CORROSION REQUIREMENTS**

RED RUST: 840

WHITE CORRIOSION: 240

**COATING THICKNESS REQUIREMENTS**

BASECOAT: MIN THICKNESS: .0003 MAX THICKNESS: .0004

TOPCOAT: MIN THICKNESS: .0002 MAX THICKNESS: .0003

**STRESS RELIEF**

NOT REQUIRED

**QUALITY CONTROL**

VISUALLY INSPECT FOR UNIFORMITY OF COLOR & SURFACE APPEARANCE, FREEDOM FROM TEARS, BARE SPOTS, POWDERY FILM. SLOUGHING OFF OF FILM & BLISTERING

**PROCESS TO**

PRINT DATE:

3/7/2018