

ITW SHAKEPROOF INDUSTRIAL PRODUCTS

FINISH
CODE

REVISION
LEVEL

BRIEF DESCRIPTION:

MU-0 EZINC-BAKE-OD-SEALER

MU

0

REV DATE: 4/1/2007

GENERAL DESCRIPTION

.00015 MIN ELECTROPLATED ZINC, OLIVE DRAB CHROMATE WITH BENCHMARK LQ-41 FILM OR EQUIVALENT ORGANIC SEALER

APPEARANCE

UNIFORM OLIVE DRAB COLOR

ADHESION AND DUCTILITY

TO BE TESTED IN ACCORDANCE TO ASTM B571 (SCOTCH TAPE TEST)

CORROSION REQUIREMENTS

RED RUST: 120

WHITE CORRIOSION: 96

SALT SPRAY TESTS TO BE PERFORMED PER ASTM B117

COATING THICKNESS REQUIREMENTS

MIN THICKNESS: .00015 MAX THICKNESS: .00035
THICKNESS SHALL BE TESTED PER ASTM E376

STRESS RELIEF

PARTS TO BE BAKED AT 400 DEGREES F FOR 4 HOURS WITHIN 1 HOUR OF BASE PLATING

QUALITY CONTROL

VISUALLY INSPECT FOR UNIFORMITY OF COLOR & SURFACE APPEARANCE, FREEDOM FROM TEARS, BARE SPOTS, POWDERY FILM. SLOUGHING OFF OF FILM & BLISTERING

PROCESS TO

GE F70B13D24

PRINT DATE:

6/3/2016