

ITW SHAKEPROOF INDUSTRIAL PRODUCTS

FINISH
CODE

REVISION
LEVEL

BRIEF DESCRIPTION:

NQ-0 EZINC-BAKE-GRN CHRMT

NQ

0

REV DATE: 4/1/2007

GENERAL DESCRIPTION

.0002 MIN ELECTROPLATED ZINC, DICHROMATE LEACHED CLEAR & GREEN DYE

APPEARANCE

GLOSSY GREEN

ADHESION AND DUCTILITY

TO BE TESTED IN ACCORDANCE TO ASTM B571 (SCOTCH TAPE TEST)

CORROSION REQUIREMENTS

RED RUST: 60

WHITE CORRIOSION: 24

SALT SPRAY TESTS TO BE PERFORMED PER ASTM B117

COATING THICKNESS REQUIREMENTS

MIN THICKNESS: .0002 MAX THICKNESS: .0004
THICKNESS TO BE TESTED PER ASTM E376

STRESS RELIEF

PARTS TO BE BAKED AT 400 DEGREES F FOR 4 HOURS WITHIN 1 HOUR OF BASE PLATING

QUALITY CONTROL

VISUALLY INSPECT FOR UNIFORMITY OF COLOR & SURFACE APPEARANCE, FREEDOM FROM TEARS, BARE SPOTS, POWDERY FILM, SLOUGHING OFF OF FILM, & BLISTERING

PROCESS TO

PRINT DATE:

6/3/2016