

# ITW SHAKEPROOF INDUSTRIAL PRODUCTS

FINISH  
CODE

REVISION  
LEVEL

**BRIEF DESCRIPTION:**

RN-0 EZINC-BAKE-BLUE-SEAL-ROHS

**RN**

**0**

REV DATE: 4/22/2016

**GENERAL DESCRIPTION**

.0003 MIN ELECTROZINC AND TRIBLUE MEDIUM BUILD WITH UNIVERSAL SEALER. !!!MUST BE ROHS COMPLIANT!!!

**APPEARANCE**

BLUE

**ADHESION AND DUCTILITY**

TO BE TESTED IN ACCORDANCE TO ASTM B571 (SCOTCH TAPE TEST)

**CORROSION REQUIREMENTS**

RED RUST: 240

WHITE CORRIOSION: 96

SALT SPRAY TESTS TO BE PERFORMED PER ASTM B117

**COATING THICKNESS REQUIREMENTS**

MIN THICKNESS: .0003      MAX THICKNESS: .0005  
THICKNESS SHALL BE TESTED PER ASTM E376

**STRESS RELIEF**

PARTS TO BE BAKED AT 400 DEGREES F FOR 4 HOURS WITHIN 1 HOUR OF BASE PLATING

**QUALITY CONTROL**

VISUALLY INSPECT FOR UNIFORMITY OF COLOR AND SURFACE APPEARANCE, FREEDOM FROM TEARS, BARE SPOTS, POWDERY FILM, SLOUGHING OFF OF FILM, AND BLISTERING

**PROCESS TO**

CHEMPLATE QUOTE 8356

PRINT DATE:

6/6/2016