

ITW SHAKEPROOF INDUSTRIAL PRODUCTS

FINISH
CODE

REVISION
LEVEL

BRIEF DESCRIPTION:

TM-0 EZINC/NI-BAKE-CHRMT-TPCT

TM

0

REV DATE: 4/1/2007

GENERAL DESCRIPTION

.0003 MIN ZINC/ NICKEL ALLOY, BAKE YELLOW DICHROMATE FILM (PS-8955-NI) & BLACK ORGANIC TOP COAT (PS-7902-B)

APPEARANCE

BLACK

ADHESION AND DUCTILITY

TO BE TESTED IN ACCORDANCE TO ASTM B571 (SCOTCH TAPE TEST)

CORROSION REQUIREMENTS

RED RUST: 500

WHITE CORRIOSION: 240

SALT SPRAY TESTS TO BE PERFORMED PER ASTM B117

COATING THICKNESS REQUIREMENTS

MIN THICKNESS: .0003 MAX THICKNESS: .0005
THICKNESS SHALL BE TESTED PER ASTM E376

STRESS RELIEF

PARTS TO BE BAKED AT 400 DEGREES F FOR 8 HOURS WITHIN 1 HOUR OF BASE PLATING

QUALITY CONTROL

VISUALLY INSPECT FOR UNIFORMITY OF COLOR AND SURFACE APPEARANCE, FREEDOM FROM TEARS, BARE SPOTS, POWDERY FILM, SLOUGHING OFF OF FILM, AND BLISTERING

PROCESS TO

CHRYSLER PS-7187

PRINT DATE:

6/7/2016