

ITW SHAKEPROOF INDUSTRIAL PRODUCTS

FINISH
CODE

REVISION
LEVEL

BRIEF DESCRIPTION:

TQ-3 ARMORGALV-TRI40-US SEAL-RoHS

TQ

3

REV DATE: 10/18/2017

GENERAL DESCRIPTION

ZINC THERMO-DIFFUSION COATING PER ARMORGALV PROCESS FOLLOWED BY TRITOP 40 AND US SEALER.
!!!MUST BE RoHS COMPLIANT!!!

APPEARANCE

GRAY

ADHESION AND DUCTILITY

PER ARMORGALV PROCESS

CORROSION REQUIREMENTS

PER ARMORGALV PROCESS

RED RUST: 1000

WHITE CORRIOSION:

COATING THICKNESS REQUIREMENTS

MIN. THICKNESS: 20 MICRONS MAX. THICKNESS: 27 MICRONS

STRESS RELIEF

NOT REQUIRED

QUALITY CONTROL

PER ARMORGALV PROCESS

PROCESS TO

PRINT DATE:

10/18/2017