

ITW SHAKEPROOF INDUSTRIAL PRODUCTS

FINISH
CODE

REVISION
LEVEL

BRIEF DESCRIPTION:

UF-2 EZINC-BAKE-CHROMAT-PTHEAD

UF

2

REV DATE: 4/1/2007

GENERAL DESCRIPTION

.002 MINIMUM ELECTROPOLATED ZINC AND YELLOW CHROMATE (ALKALINE LEACHED TO CLEAR). PAINT HEAD BLACK. USE ONLY POLY-URETHANE PAINT TO PREVENT CHIPPING.

APPEARANCE

CLEAR SILVER WHITE FINISH. TOP OF HEAD TO HAVE A SMOOTH BLACK APPEARANCE

ADHESION AND DUCTILITY

TO BE TESTED IN ACCORDANCE TO ASTM B571 (SCOTCH TAPE TEST)

CORROSION REQUIREMENTS

RED RUST: 60

WHITE CORRIOSION: 24

SALT SPRAY TESTS TO BE PERFORMED PER ASTM B117

COATING THICKNESS REQUIREMENTS

MIN THICKNESS: .0002

MAX THICKNESS: .0004

THICKNESS SHALL BE TESTED PER ASTM E376

STRESS RELIEF

PARTS TO BE BAKED AT 400 DEGREES F FOR 4 HOURS WITHIN 1 HOUR OF BASE PLATING

QUALITY CONTROL

VISUALLY INSPECT FOR UNIFORMITY OF COLOR AND SURFACE APPEARANCE, FREEDOM FROM TEARS, BARE SPOTS, POWDERY FILM, SLOUGHING OFF OF FILM, AND BLISTERING

PROCESS TO

PRINT DATE:

6/8/2016