ITW SHAKEPROOF INDUSTRIAL PRODUCTSFINISH
CODEREVISION
LEVELBRIEF DESCRIPTION:
VA-0 TIN/ZINC-BAKE-CHRMAT-SEALVA0REV DATE:4/1/2007

GENERAL DESCRIPTION

ZINC TIN ALLOY (30% TIN /70% POWDER MIX) YELLOW DICHROMATE (LEACHED TO CLEAR & SEALANT)

APPEARANCE

DULL SILVERY APPEARANCE

ADHESION AND DUCTILITY

BURNISH BY WATER POLISHING TO CONSOLIDATE THE COATING TO BE TESTED IN ACCORDANCE TO ASTM B571 (SCOTCH TAPE TEST)

CORROSION REQUIREMENTS RED RUST: 250

SALT SPRAY TESTS TO BE PERFORMED PER ASTM B117

COATING THICKNESS REQUIREMENTS

MIN THICKNESS: .0004 MAX THICKNESS: .0006 THICKNESS SHALL BE TESTED PER ASTM E376

STRESS RELIEF

NOT REQUIRED

QUALITY CONTROL

VISUALLY INSPECT FOR UNIFORMITY OF COLOR AND SURFACE APPEARANCE, FREEDOM FROM TEARS, BARE SPOTS, POWDERY FILM, SLOUGHING OFF OF FILM, AND BLISTERING

PROCESS TO

CHRYSLER PS-8956M C40

PRINT DATE:

6/8/2016

WHITE CORRIOSION: <u>120</u>