

ITW SHAKEPROOF INDUSTRIAL PRODUCTS

FINISH
CODE

REVISION
LEVEL

BRIEF DESCRIPTION:

YU-0 EZINC-SILVER-SEAL-ROHS

YU

0

REV DATE: 7/16/2008

GENERAL DESCRIPTION

.0003 MIN. ELECTRO ZINC WITH CLEAR TRIVALENT CHROMATE FOLLOWED BY SILICATE SEALANT.
!!!MUST BE ROHS COMPLIANT!!!

APPEARANCE

SILVERY APPEARANCE

ADHESION AND DUCTILITY

TO BE TESTED IN ACCORDANCE TO ASTM B571 (SCOTCH TAPE TEST)

CORROSION REQUIREMENTS

RED RUST: 500

WHITE CORRIOSION: 120

SALT SPRAY TEST TO BE PERFORMED PER ASTM B117

COATING THICKNESS REQUIREMENTS

.0003 MIN. THICKNESS .0005 MAX. THICKNESS TESTED PER ASTM E376

STRESS RELIEF

PARTS TO BE BAKED AT 400 DEGREES F FOR 4 HOURS WITHIN 1 HOUR OF BASE PLATING

QUALITY CONTROL

VISUALLY INSPECT FOR UNIFORMITY OF COLOR AND SURFACE APPEARANCE, FREEDOM FROM TEARS, BARE SPOTS, POWDERY FILM, SLOUGHING OFF OF FILM, AND BLISTERING

PROCESS TO

PRINT DATE:

6/14/2016